

# Arcol<sup>®</sup> Polyol PPG 2000

## General Properties and Applications

Arcol<sup>®</sup> Polyol PPG 2000 is a bifunctional polyether polyol for the production of polyurethane products.

## Sampling

Moisture access should be prevented when taking product samples.

| Specification Property | Value       | Unit of measurement | Method        |
|------------------------|-------------|---------------------|---------------|
| Hydroxyl number        | 54.7 - 57.5 | mg KOH/g            | PET – 11 – 01 |
| Water content          | max. 0.050  | % by wt.            | PET – 19 – 01 |
| Acidity                | max. 0.020  | mg KOH/g            | PET – 01 – 01 |
| Viscosity at 25 °C     | 325 - 365   | mPa·s               | PET – 10 – 01 |

| Other Data* Property | Value        | Unit of measurement | Method    |
|----------------------|--------------|---------------------|-----------|
| Density at 20 °C     | approx. 1.01 | g/cm <sup>3</sup>   | DIN 51757 |

\* These values provide general information and are not part of the product specification

## Storage

Recommended storage temperature (°C): 20 – 40

Shelf life (ex works): 12 months if stored in sealed containers

## Labeling and REACH applications

This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating to the current classification and labeling, applications and processing methods and further data relevant to safety can be found in the currently valid Safety Data Sheet.



# Arcol<sup>®</sup> Polyol PPG 2000

---

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

---

Editor: Business Unit Polyurethanes  
Covestro AG  
Kaiser-Wilhelm-Allee 60  
51373 Leverkusen, Germany  
[www.covestro.com](http://www.covestro.com)

**Contact :**  
Business Unit Polyurethanes  
e-mail: [pur@covestro.com](mailto:pur@covestro.com)